CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
# 4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

## TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

| | | |
|---|---|---|
| **Lab ID** | : | **CP-2019-08-30-115** **Date: 13-08-19** |
| **Customer** | : | Assistant Executive Engineer, Yelahanka Sub Division, BBMP, |
| **Address** | : | Yelahanka Sub Division, BBMP, Bangalore. |
| **Project Name** | : | Construction of Grill Work for Boating at Yelahanka Lake in Ward No-01 of Yelahanka Sub Division. |
| **Agency** | : | Sri.Balaji G, No:600, Vakkaligara Street, Yelahanka, Bangalore-560064. |
| **Customer's Reference** | : | EE(YNK.D)E-PMT-19/W.O/56/2018-19 |
| **Source of Sample** | : | Sample supplied by Agency |
| **Sample Condition** | : | Satisfactory |
| **Date of Receipt** | : | 08-08-19 |
| **Sample Type** | : | Birla Super 53grade |
| **Reference to BIS codes** | : | IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification ,<br>IS 4031 (Part 1,2 3,4,5, 6,11):1988<br>IS 4031 Part 1 DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4<br>IS 4031 Part 2, Determination of Fineness by Blaine Air Permeability Method, Clause 5<br>IS 4031 Part 3, Determination of Soundness, Clause 5,Clause 6<br>IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5<br>IS 4031 Part 5, Determination of Initial & Final Setting Time, Clause 5<br>IS 4031 Part 11,DETERMINATION OF DENSITY , Clause 6 |
| **Date of test** | : | 09-08-19 |
| **Environmental Conditions during test** | : | Temperature: 26°C<br>Humidity: 72% |

| Sl.No. | Physical properties | Results | Requirement as per IS 12269: 2013 |
|---|---|---|---|
| 1 | Fineness by dry sieving (%) | 2.89 | – |
| 2 | Finess by Air permeablity method ($m^2$/kg,Min) | 298.6 | 225$m^2$/kg, Min |
| 3 | Density (gm/cc) | 3.11 | – |
| 4 | Standard Consistency (%) | 2800.0% | Not specified |
| 5 | Initial Setting time | 165 minutes | Not less than 30 minutes |
| 6 | Final Setting time | 266 minutes | Not more than 600 minutes |
| 7 | Soundness (Le Chatelier's Method) | 2mm | Not more than 10 mm |

**Note:**

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

AE

AE-1

**FOR CIVIL Pro.**

**R RUDRAPRASAD**
Authorized Signatory
**Technical Manager**

CIVIL Pro Sig..... Date..... BANGALORE



****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner

Format No: CP/TF/01

## TEST REPORT ON COARSE AGGREGATES

| | | |
|---|---|---|
| **Lab ID** | : | **CP-2019-08-30-115** **Date: 10-08-19** |
| **Customer** | : | Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore. |
| **Address** | : | Yelahanka Sub Division, BBMP, Bangalore. |
| **Project Name** | : | Construction of Grill Work for Boating at Yelahanka Lake in Ward No-01 of Yelahanka Sub Division. |
| **Agency** | : | Sri.Balaji G, No:600, Vakkaligara Street, Yelahanka, Bangalore-560064. |
| **Customer Reference** | : | EE(YNK.D)E-PMT-19/W.O/56/2018-19 |
| **Source of Sample** | : | Sample supplied by Agency |
| **Sample Condition** | : | Satisfactory |
| **Date of Receipt** | : | 08-08-19 |
| **Sample Type/ Size** | : | 20mm down size coarse aggregate |
| **Reference to BIS codes** | : | IS: 383:2016 (Specification for Coarse and fine Aggregates )<br>IS: 2386 :1963(Part - 1,3,4) RA2011<br>IS 2386 Part 1: Particle Size and Shape<br>IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption<br>IS 2386 Part 4: Mechanical Properties |
| **Date of test** | : | 08-08-19 |

**SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 20MM DOWN COARSE AGGREGATE:**

**Total weight taken : 5000 grams**

| Sample No. | Sieve No. | Weight Retained in gms | Cumulative Weight Retained in gms | % Cumulative Weight Retained | % Passing | Required as per IS 383:2016 |
|---|---|---|---|---|---|---|
| 1 | 40 mm | 0 | 0 | 0 | 100 | 100 |
| 2 | 20 mm | 297 | 297 | 5.9 | 94.1 | 90-100 |
| 3 | 10 mm | 2643 | 2940 | 58.8 | 41.2 | 25-55 |
| 4 | 4.75 mm | 1813 | 4753 | 95.1 | 4.9 | 0-10 |
| 5 | Pan | 247 | 5000 | 100 | 0 | _ |

AE

AE-1



CIVIL Pro Sig..... Date..... BANGALORE



Scanned by CamScanner